



V300 Trinsic™ Series Thermal Chart

Revision Date: 4/7/2023

IG Thickness	Exterior Glass	Spacer	Interior Glass	Gas Fill	No Grids					Flat Grids					Sculptured Grids				
					U-Value	SHGC	VLT	Energy Star 6.0	Title 24	U-Value	SHGC	VLT	Energy Star 6.0	Title 24	U-Value	SHGC	VLT	Energy Star 6.0	Title 24
Horizontal Slider																			
3/4"	SunCoat	Intercept	Clear	Air	0.32	0.31	0.55	-	-	0.32	0.28	0.49	-	-	0.34	0.25	0.43	S	-
3/4"	SunCoat	Intercept	Clear	Argon	0.29	0.30	0.55	NC	-	0.29	0.27	0.49	NC	-	0.31	0.25	0.43	S	-
3/4"	SunCoatMax	Intercept	Clear	Air	0.32	0.23	0.48	S	-	0.32	0.21	0.43	S	-	0.34	0.19	0.38	S	-
3/4"	SunCoatMax	Intercept	Clear	Argon	0.29	0.22	0.48	NC, SC, S	Yes	0.29	0.20	0.43	N, SC, S	Yes	0.30	0.18	0.38	NC, SC, S	Yes
3/4"	SunCoat	Intercept	4th Surface	Air	0.27	0.30	0.54	N, NC	-	0.27	0.27	0.48	N, NC	-	0.29	0.24	0.43	NC, SC, S	-
3/4"	SunCoat	Intercept	4th Surface	Argon	0.25	0.30	0.54	N, NC	-	0.25	0.27	0.48	N, NC	-	0.26	0.24	0.43	N, NC, SC, S	-
3/4"	SunCoatMax	Intercept	4th Surface	Air	0.27	0.20	0.47	N, NC, SC, S	Yes	0.27	0.19	0.42	N, NC, SC, S	Yes	0.28	0.17	0.37	NC, SC, S	Yes
3/4"	SunCoatMax	Intercept	4th Surface	Argon	0.25	0.20	0.47	N, NC, SC, S	Yes	0.25	0.18	0.42	N, NC, SC, S	Yes	0.26	0.17	0.37	N, NC, SC, S	Yes
3/4"	SunCoat	Foam	Clear	Air	0.32	0.31	0.55	-	-	0.32	0.28	0.49	-	-	0.34	0.25	0.43	S	-
3/4"	SunCoat	Foam	Clear	Argon	0.29	0.30	0.55	NC	-	0.29	0.27	0.49	NC	-	0.30	0.25	0.43	NC, SC, S	-
3/4"	SunCoatMax	Foam	Clear	Air	0.32	0.23	0.48	S	-	0.32	0.21	0.43	S	-	0.34	0.19	0.38	S	-
3/4"	SunCoatMax	Foam	Clear	Argon	0.28	0.22	0.48	NC, SC, S	Yes	0.28	0.20	0.43	NC, SC, S	Yes	0.30	0.18	0.38	NC, SC, S	Yes
3/4"	SunCoat	Foam	4th Surface	Air	0.27	0.30	0.54	N, NC	-	0.27	0.27	0.48	N, NC	-	0.28	0.24	0.43	NC, SC, S	-
3/4"	SunCoat	Foam	4th Surface	Argon	0.24	0.30	0.54	N, NC	-	0.24	0.27	0.48	N, NC	-	0.26	0.24	0.43	N, NC, SC, S	-
3/4"	SunCoatMax	Foam	4th Surface	Air	0.27	0.20	0.47	N, NC, SC, S	Yes	0.27	0.19	0.42	N, NC, SC, S	Yes	0.28	0.17	0.37	NC, SC, S	Yes
3/4"	SunCoatMax	Foam	4th Surface	Argon	0.24	0.20	0.47	N, NC, SC, S	Yes	0.24	0.18	0.42	N, NC, SC, S	Yes	0.25	0.17	0.37	N, NC, SC, S	Yes
Single Hung																			
3/4"	SunCoat	Intercept	Clear	Air	0.32	0.31	0.55	-	-	0.32	0.28	0.49	-	-	0.34	0.25	0.43	S	-
3/4"	SunCoat	Intercept	Clear	Argon	0.29	0.30	0.55	NC	-	0.29	0.27	0.49	NC	-	0.30	0.25	0.43	NC, SC, S	-
3/4"	SunCoatMax	Intercept	Clear	Air	0.32	0.23	0.48	S	-	0.32	0.21	0.43	S	-	0.34	0.19	0.38	S	-
3/4"	SunCoatMax	Intercept	Clear	Argon	0.29	0.22	0.48	NC, SC, S	Yes	0.29	0.20	0.43	NC, SC, S	Yes	0.30	0.18	0.38	NC, SC, S	Yes
3/4"	SunCoat	Intercept	4th Surface	Air	0.27	0.30	0.54	N, NC	-	0.27	0.27	0.48	N, NC	-	0.29	0.24	0.43	NC, SC, S	-
3/4"	SunCoat	Intercept	4th Surface	Argon	0.25	0.30	0.54	N, NC	-	0.25	0.27	0.48	N, NC	-	0.26	0.24	0.43	N, NC, SC, S	-
3/4"	SunCoatMax	Intercept	4th Surface	Air	0.27	0.20	0.47	N, NC, SC, S	Yes	0.27	0.19	0.42	N, NC, SC, S	Yes	0.28	0.17	0.37	NC, SC, S	Yes
3/4"	SunCoatMax	Intercept	4th Surface	Argon	0.24	0.20	0.47	N, NC, SC, S	Yes	0.24	0.18	0.42	N, NC, SC, S	Yes	0.26	0.17	0.37	N, NC, SC, S	Yes
3/4"	SunCoat	Foam	Clear	Air	0.32	0.31	0.55	-	-	0.32	0.28	0.49	-	-	0.34	0.25	0.43	S	-
3/4"	SunCoat	Foam	Clear	Argon	0.29	0.30	0.55	NC	-	0.29	0.27	0.49	NC	-	0.30	0.25	0.43	NC, SC, S	-
3/4"	SunCoatMax	Foam	Clear	Air	0.32	0.23	0.48	S	-	0.32	0.21	0.43	S	-	0.34	0.19	0.38	S	-
3/4"	SunCoatMax	Foam	Clear	Argon	0.28	0.22	0.48	NC, SC, S	Yes	0.28	0.20	0.43	NC, SC, S	Yes	0.30	0.18	0.38	NC, SC, S	Yes
3/4"	SunCoat	Foam	4th Surface	Air	0.27	0.30	0.54	N, NC	-	0.27	0.27	0.48	N, NC	-	0.28	0.24	0.43	NC, SC, S	-
3/4"	SunCoat	Foam	4th Surface	Argon	0.24	0.30	0.54	N, NC	-	0.24	0.27	0.48	N, NC	-	0.26	0.24	0.43	N, NC, SC, S	-
3/4"	SunCoatMax	Foam	4th Surface	Air	0.27	0.20	0.47	N, NC, SC, S	Yes	0.27	0.19	0.42	N, NC, SC, S	Yes	0.28	0.17	0.37	N, NC, SC, S	Yes
3/4"	SunCoatMax	Foam	4th Surface	Argon	0.24	0.20	0.47	N, NC, SC, S	Yes	0.24	0.18	0.42	N, NC, SC, S	Yes	0.25	0.17	0.37	N, NC, SC, S	Yes
Picture Window (direct set)																			
1"	SunCoat	Intercept	Clear	Air	0.33	0.32	0.57	-	-	0.33	0.29	0.51	-	-	0.33	0.26	0.45	-	-
1"	SunCoat	Intercept	Clear	Argon	0.29	0.31	0.57	NC	-	0.29	0.28	0.51	NC	-	0.29	0.26	0.45	NC	-
1"	SunCoatMax	Intercept	Clear	Air	0.32	0.23	0.50	S	-	0.32	0.21	0.45	S	-	0.32	0.19	0.40	S	-
1"	SunCoatMax	Intercept	Clear	Argon	0.29	0.23	0.50	NC, SC, S	Yes	0.29	0.21	0.45	NC, SC, S	Yes	0.29	0.19	0.40	NC, SC, S	Yes
1"	SunCoat	Intercept	4th Surface	Air	0.27	0.31	0.56	N, NC	-	0.27	0.28	0.50	N, NC	-	0.27	0.25	0.44	N, NC, SC, S	-
1"	SunCoat	Intercept	4th Surface	Argon	0.24	0.31	0.56	N, NC	-	0.24	0.28	0.50	N, NC	-	0.24	0.25	0.44	N, NC, SC, S	-
1"	SunCoatMax	Intercept	4th Surface	Air	0.26	0.21	0.49	N, NC, SC, S	Yes	0.26	0.19	0.43	N, NC, SC, S	Yes	0.26	0.17	0.39	N, NC, SC, S	Yes
1"	SunCoatMax	Intercept	4th Surface	Argon	0.24	0.21	0.49	N, NC, SC, S	Yes	0.24	0.19	0.43	N, NC, SC, S	Yes	0.24	0.17	0.39	N, NC, SC, S	Yes
1"	SunCoat	Foam	Clear	Air	0.32	0.32	0.50	-	-	0.32	0.29	0.51	-	-	0.32	0.26	0.45	-	-
1"	SunCoat	Foam	Clear	Argon	0.28	0.31	0.57	S	-	0.28	0.28	0.51	NC	-	0.28	0.26	0.45	NC	-
1"	SunCoatMax	Foam	Clear	Air	0.32	0.23	0.50	S	-	0.32	0.21	0.45	S	-	0.32	0.19	0.40	S	-
1"	SunCoatMax	Foam	Clear	Argon	0.28	0.23	0.50	NC, SC, S	Yes	0.28	0.21	0.48	NC, SC, S	Yes	0.28	0.19	0.40	NC, SC, S	Yes
1"	SunCoat	Foam	4th Surface	Air	0.26	0.31	0.56	N, NC	-	0.26	0.28	0.50	N, NC	-	0.26	0.25	0.44	N, NC, SC, S	-
1"	SunCoat	Foam	4th Surface	Argon	0.24	0.31	0.56	N, NC	-	0.24	0.28	0.50	N, NC	-	0.24	0.25	0.44	N, NC, SC, S	-
1"	SunCoatMax	Foam	4th Surface	Air	0.26	0.21	0.49	N, NC, SC, S	Yes	0.26	0.19	0.43	N, NC, SC, S	Yes	0.26	0.17	0.39	N, NC, SC, S	Yes

Due to continual product development, data presented is subject to change at any time. Available components may vary by manufacturing location.



V300 Trinsic™ Series Thermal Chart

Revision Date: 4/7/2023

IG Thickness	Exterior Glass	Spacer	Interior Glass	Gas Fill	No Grids					Flat Grids					Sculptured Grids				
					U-Value	SHGC	VLT	Energy Star 6.0	Title 24	U-Value	SHGC	VLT	Energy Star 6.0	Title 24	U-Value	SHGC	VLT	Energy Star 6.0	Title 24
1"	SunCoatMax	Foam	4th Surface	Argon	0.23	0.21	0.49	N, NC, SC, S	Yes	0.23	0.19	0.43	N, NC, SC, S	Yes	0.23	0.17	0.39	N, NC, SC, S	Yes
Picture Window (slider frame)																			
3/4"	SunCoat	Intercept	Clear	Air	0.31	0.32	0.57	-	-	0.31	0.29	0.51	-	-	0.33	0.26	0.45	-	-
3/4"	SunCoat	Intercept	Clear	Argon	0.27	0.31	0.57	N, NC	-	0.27	0.28	0.51	N, NC	-	0.29	0.26	0.45	N	-
3/4"	SunCoatMax	Intercept	Clear	Air	0.31	0.23	0.50	S	-	0.31	0.21	0.45	S	-	0.33	0.19	0.40	S	-
3/4"	SunCoatMax	Intercept	Clear	Argon	0.27	0.23	0.50	N, NC, SC, S	Yes	0.27	0.21	0.45	N, NC, SC, S	Yes	0.29	0.19	0.40	NC, SC, S	Yes
3/4"	SunCoat	Intercept	4th Surface	Air	0.26	0.31	0.56	N, NC	-	0.26	0.28	0.50	N, NC	-	0.27	0.25	0.44	N, NC, SC, S	-
3/4"	SunCoat	Intercept	4th Surface	Argon	0.23	0.31	0.56	N, NC	-	0.23	0.28	0.50	N, NC	-	0.25	0.25	0.44	N, NC, SC, S	-
3/4"	SunCoatMax	Intercept	4th Surface	Air	0.25	0.21	0.49	N, NC, SC, S	Yes	0.25	0.19	0.44	N, NC, SC, S	Yes	0.27	0.17	0.39	N, NC, SC, S	Yes
3/4"	SunCoatMax	Intercept	4th Surface	Argon	0.23	0.21	0.49	N, NC, SC, S	Yes	0.23	0.19	0.44	N, NC, SC, S	Yes	0.24	0.17	0.39	N, NC, SC, S	Yes
3/4"	SunCoat	Foam	Clear	Air	0.31	0.32	0.57	-	-	0.31	0.29	0.51	-	-	0.33	0.26	0.45	-	-
3/4"	SunCoat	Foam	Clear	Argon	0.27	0.31	0.57	N, NC	-	0.27	0.28	0.51	N, NC	-	0.29	0.26	0.45	NC	-
3/4"	SunCoatMax	Foam	Clear	Air	0.31	0.23	0.50	S	-	0.31	0.21	0.45	S	-	0.33	0.19	0.40	S	-
3/4"	SunCoatMax	Foam	Clear	Argon	0.27	0.23	0.50	N, NC, SC, S	Yes	0.27	0.21	0.45	N, NC, SC, S	Yes	0.29	0.19	0.40	NC, SC, S	Yes
3/4"	SunCoat	Foam	4th Surface	Air	0.25	0.31	0.56	N, NC	-	0.25	0.28	0.50	N, NC	-	0.27	0.25	0.44	N, NC, SC, S	-
3/4"	SunCoat	Foam	4th Surface	Argon	0.23	0.31	0.56	N, NC	-	0.23	0.28	0.50	N, NC	-	0.24	0.25	0.44	N, NC, SC, S	-
3/4"	SunCoatMax	Foam	4th Surface	Air	0.25	0.21	0.49	N, NC, SC, S	Yes	0.25	0.19	0.44	N, NC, SC, S	Yes	0.27	0.17	0.39	N, NC, SC, S	Yes
3/4"	SunCoatMax	Foam	4th Surface	Argon	0.23	0.21	0.49	N, NC, SC, S	Yes	0.23	0.19	0.44	N, NC, SC, S	Yes	0.24	0.17	0.39	N, NC, SC, S	Yes
Casement																			
7/8"	SunCoat	Intercept	Clear	Air	0.31	0.28	0.50	-	-	0.31	0.26	0.45	-	-	0.31	0.23	0.41	S	-
7/8"	SunCoat	Intercept	Clear	Argon	0.28	0.28	0.50	NC	-	0.28	0.25	0.45	NC, SC, S	-	0.28	0.23	0.41	NC, SC, S	Yes
7/8"	SunCoatMax	Intercept	Clear	Air	0.31	0.21	0.44	S	-	0.31	0.19	0.40	S	-	0.31	0.17	0.36	S	-
7/8"	SunCoatMax	Intercept	Clear	Argon	0.28	0.20	0.44	NC, SC, S	Yes	0.28	0.19	0.40	NC, SC, S	Yes	0.28	0.17	0.36	NC, SC, S	Yes
7/8"	SunCoat	Intercept	4th Surface	Air	0.26	0.28	0.49	N, NC	-	0.26	0.25	0.44	N, NC, SC, S	-	0.26	0.23	0.40	N, NC, SC, S	Yes
7/8"	SunCoat	Intercept	4th Surface	Argon	0.24	0.27	0.49	N, NC	-	0.24	0.25	0.44	N, NC, SC, S	-	0.24	0.23	0.40	N, NC, SC, S	Yes
7/8"	SunCoatMax	Intercept	4th Surface	Air	0.26	0.19	0.43	N, NC, SC, S	Yes	0.26	0.17	0.39	N, NC, SC, S	Yes	0.26	0.16	0.35	N, NC, SC, S	Yes
7/8"	SunCoatMax	Intercept	4th Surface	Argon	0.24	0.18	0.43	N, NC, SC, S	Yes	0.24	0.17	0.39	N, NC, SC, S	Yes	0.24	0.16	0.35	N, NC, SC, S	Yes
7/8"	SunCoat	Foam	Clear	Air	0.30	0.28	0.50	NC	-	0.30	0.26	0.45	NC	-	0.30	0.23	0.41	NC, SC, S	Yes
7/8"	SunCoat	Foam	Clear	Argon	0.27	0.28	0.50	N, NC	-	0.27	0.25	0.45	N, NC, SC, S	-	0.27	0.23	0.41	N, NC, SC, S	Yes
7/8"	SunCoatMax	Foam	Clear	Air	0.30	0.21	0.44	NC, SC, S	Yes	0.30	0.19	0.40	NC, SC, S	Yes	0.30	0.17	0.36	NC, SC, S	Yes
7/8"	SunCoatMax	Foam	Clear	Argon	0.27	0.20	0.44	N, NC, SC, S	Yes	0.27	0.19	0.40	N, NC, SC, S	Yes	0.27	0.17	0.36	N, NC, SC, S	Yes
7/8"	SunCoat	Foam	4th Surface	Air	0.26	0.28	0.49	N, NC	-	0.26	0.25	0.44	N, NC, SC, S	-	0.26	0.23	0.40	N, NC, SC, S	Yes
7/8"	SunCoat	Foam	4th Surface	Argon	0.24	0.27	0.49	N, NC	-	0.24	0.25	0.44	N, NC, SC, S	-	0.24	0.23	0.40	N, NC, SC, S	Yes
7/8"	SunCoatMax	Foam	4th Surface	Air	0.25	0.19	0.43	N, NC, SC, S	Yes	0.25	0.17	0.39	N, NC, SC, S	Yes	0.25	0.16	0.35	N, NC, SC, S	Yes
7/8"	SunCoatMax	Foam	4th Surface	Argon	0.23	0.18	0.43	N, NC, SC, S	Yes	0.23	0.17	0.39	N, NC, SC, S	Yes	0.23	0.16	0.35	N, NC, SC, S	Yes
Awning																			
7/8"	SunCoat	Intercept	Clear	Air	0.32	0.28	0.50	-	-	0.32	0.26	0.45	-	-	0.32	0.23	0.41	S	-
7/8"	SunCoat	Intercept	Clear	Argon	0.29	0.28	0.50	NC	-	0.29	0.25	0.45	NC, SC, S	-	0.29	0.23	0.41	NC, SC, S	Yes
7/8"	SunCoatMax	Intercept	Clear	Air	0.32	0.21	0.44	S	-	0.32	0.19	0.40	S	-	0.32	0.17	0.36	S	-
7/8"	SunCoatMax	Intercept	Clear	Argon	0.29	0.20	0.44	NC, SC, S	Yes	0.29	0.19	0.40	NC, SC, S	Yes	0.29	0.17	0.36	NC, SC, S	Yes
7/8"	SunCoat	Intercept	4th Surface	Air	0.28	0.28	0.49	NC	-	0.28	0.25	0.44	NC, SC, S	-	0.28	0.23	0.40	NC, SC, S	Yes
7/8"	SunCoat	Intercept	4th Surface	Argon	0.25	0.27	0.49	N, NC	-	0.25	0.25	0.44	N, NC, SC, S	-	0.25	0.23	0.40	N, NC, SC, S	Yes
7/8"	SunCoatMax	Intercept	4th Surface	Air	0.27	0.19	0.43	N, NC, SC, S	Yes	0.27	0.17	0.39	N, NC, SC, S	Yes	0.27	0.16	0.35	N, NC, SC, S	Yes
7/8"	SunCoatMax	Intercept	4th Surface	Argon	0.25	0.18	0.43	N, NC, SC, S	Yes	0.25	0.17	0.39	N, NC, SC, S	Yes	0.25	0.16	0.35	N, NC, SC, S	Yes
7/8"	SunCoat	Foam	Clear	Air	0.31	0.28	0.50	-	-	0.31	0.26	0.45	-	-	0.31	0.23	0.41	S	-
7/8"	SunCoat	Foam	Clear	Argon	0.28	0.28	0.50	NC	-	0.28	0.25	0.45	NC, SC, S	-	0.28	0.23	0.41	NC, SC, S	Yes
7/8"	SunCoatMax	Foam	Clear	Air	0.31	0.21	0.44	S	-	0.31	0.19	0.40	S	-	0.31	0.17	0.36	S	-
7/8"	SunCoatMax	Foam	Clear	Argon	0.28	0.20	0.44	NC, SC, S	Yes	0.28	0.19	0.40	NC, SC, S	Yes	0.28	0.17	0.36	NC, SC, S	Yes
7/8"	SunCoat	Foam	4th Surface	Air	0.27	0.28	0.49	N, NC	-	0.27	0.25	0.44	N, NC, SC, S	-	0.27	0.23	0.40	N, NC, SC, S	Yes
7/8"	SunCoat	Foam	4th Surface	Argon	0.25	0.27	0.49	N, NC, SC, S	-	0.25	0.25	0.44	N, NC, SC, S	-	0.25	0.23	0.40	N, NC, SC, S	Yes

Due to continual product development, data presented is subject to change at any time. Available components may vary by manufacturing location.



V300 Trinsic™ Series Thermal Chart

Revision Date: 4/7/2023

IG Thickness	Exterior Glass	Spacer	Interior Glass	Gas Fill	No Grids					Flat Grids					Sculptured Grids				
					U-Value	SHGC	VLТ	Energy Star 6.0	Title 24	U-Value	SHGC	VLТ	Energy Star 6.0	Title 24	U-Value	SHGC	VLТ	Energy Star 6.0	Title 24
7/8"	SunCoatMax	Foam	4th Surface	Air	0.27	0.19	0.43	N, NC, SC, S	Yes	0.27	0.17	0.39	N, NC, SC, S	Yes	0.27	0.16	0.35	N, NC, SC, S	Yes
7/8"	SunCoatMax	Foam	4th Surface	Argon	0.24	0.18	0.43	N, NC, SC, S	Yes	0.24	0.17	0.39	N, NC, SC, S	Yes	0.24	0.16	0.35	N, NC, SC, S	Yes
Sliding Patio Door																			
1"	SunCoat	Intercept	Clear	Air	0.33	0.30	0.56	-	-	0.33	0.27	0.50	-	-	0.33	0.24	0.43	S	-
1"	SunCoat	Intercept	Clear	Argon	0.29	0.30	0.56	NC	-	0.29	0.27	0.50	NC	-	0.29	0.23	0.43	NC, SC, S	Yes
1"	SunCoatMax	Intercept	Clear	Air	0.32	0.22	0.52	S	-	0.32	0.20	0.46	S	-	0.32	0.18	0.40	S	-
1"	SunCoatMax	Intercept	Clear	Argon	0.28	0.22	0.52	NC, SC, S	Yes	0.28	0.20	0.46	NC, SC, S	Yes	0.28	0.18	0.40	NC, SC, S	Yes
1"	SunCoat	Intercept	4th Surface	Air	0.26	0.30	0.56	N, NC	-	0.26	0.26	0.49	N, NC	-	0.26	0.23	0.42	N, NC, SC, S	Yes
1"	SunCoat	Intercept	4th Surface	Argon	0.24	0.29	0.56	N, NC	-	0.24	0.26	0.49	N, NC	-	0.24	0.23	0.42	N, NC, SC, S	Yes
1"	SunCoatMax	Intercept	4th Surface	Air	0.26	0.22	0.51	N, NC, SC, S	Yes	0.26	0.20	0.45	N, NC, SC, S	Yes	0.26	0.17	0.39	N, NC, SC, S	Yes
1"	SunCoatMax	Intercept	4th Surface	Argon	0.24	0.22	0.51	N, NC, SC, S	Yes	0.24	0.20	0.45	N, NC, SC, S	Yes	0.24	0.17	0.39	N, NC, SC, S	Yes
1"	SunCoat	Foam	Clear	Air	0.32	0.30	0.56	-	-	0.32	0.27	0.50	-	-	0.32	0.24	0.43	S	-
1"	SunCoat	Foam	Clear	Argon	0.29	0.30	0.56	NC	-	0.29	0.27	0.50	NC	-	0.29	0.23	0.43	NC, SC, S	Yes
1"	SunCoatMax	Foam	Clear	Air	0.32	0.22	0.52	S	-	0.32	0.20	0.46	S	-	0.32	0.18	0.40	S	-
1"	SunCoatMax	Foam	Clear	Argon	0.28	0.22	0.52	NC, SC, S	Yes	0.28	0.20	0.46	NC, SC, S	Yes	0.28	0.18	0.40	NC, SC, S	Yes
1"	SunCoat	Foam	4th Surface	Air	0.26	0.30	0.56	N, NC	-	0.26	0.26	0.49	N, NC	-	0.26	0.23	0.42	N, NC, SC, S	Yes
1"	SunCoat	Foam	4th Surface	Argon	0.24	0.29	0.56	N, NC	-	0.24	0.26	0.49	N, NC	-	0.24	0.23	0.42	N, NC, SC, S	Yes
1"	SunCoatMax	Foam	4th Surface	Air	0.26	0.22	0.51	N, NC, SC, S	Yes	0.26	0.20	0.45	N, NC, SC, S	Yes	0.26	0.17	0.39	N, NC, SC, S	Yes
1"	SunCoatMax	Foam	4th Surface	Argon	0.24	0.22	0.51	N, NC, SC, S	Yes	0.24	0.20	0.45	N, NC, SC, S	Yes	0.24	0.17	0.39	N, NC, SC, S	Yes

Due to continual product development, data presented is subject to change at any time. Available components may vary by manufacturing location.